BEST AVAILABLE COP

PATENT ABSTRACTS OF JAPAN

(11) Publication number:

57-034661

(43) Date of publication of application: 25.02.1982

(51) Int. CI.

H01M 4/08

(21) Application number : **55-109534**

(71) Applicant: HITACHI MAXELL LTD

(22) Date of filing:

09. 08. 1980

(72) Inventor: ASADA AKIRA


(54) MANUFACTURE OF SILVER OXIDE BATTERY


(57) Abstract:

PURPOSE: To prevent any increase in the internal resistance of a silver oxide battery by subjecting a positive electrode body, which consists of a silver oxide layer, and an argentous oxide layer and a silver layer that are formed over the periphery of the silver oxide layer by reduction, to a water-repellent treatment so as to make up to the silver oxide layer to be impregnated with a water repellent, and removing the water repellent contained in both the argentous oxide layer and the silver layer.

CONSTITUTION: A positive electrode body 1, which is prepared by forming an argentous oxide layer 3 and a silver layer 4, in that order, over the periphery of a silver oxide layer 2, is immersed in a liquid containing a water repellent so as to make up to the silver oxide layer 2 to be

impregnated with the water repellent through





[Date of request for examination]

[Date of sending the examiner's decision

of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998, 2003 Japan Patent Office